

Anna Quarries Inc. Aggregate Gradations

Grad No.

Sieve Size and Percent Passing

Fine Aggregate

	3/8	No.4	No. 8	No.10	No.16	No.30	No.40	No.50	No.80	No.100	No.200
FM-1 (Man. Sand)	100	97 ± 3			65 ± 20			16 ± 13		8 ± 5	
FM-5 (Turkey Grit)	100	92 ± 8								20 ± 20	15 ± 15
FA-20	100	97 ± 3	80 ± 20		50 ± 15			19 ± 11		10 ± 7	4 ± 4
FA-21	100	97 ± 3	80 ± 20		57 ± 18			30 ± 10		20 ± 10	9 ± 9

AG Lime

Normal

For Gradation and CCE, MG values plus Correction Factors see Illinois Voluntary Limestone Program Producer Information

Fine

Produced By: The Illinois Department of Agriculture / Transportaion

(Link)